切削参数参考表
Recommended Milling Conditions

加工材料 Work Material		高硬度钢 Hardened Steels STAVAX・SKD61 (～52HRC)				高硬度钢 Hardened Steels SKD11・ELMAX (～62HRC)				高速钢 High Speed Steels SKH・HAP (～68HRC)			
(R)球头半径 Radius	颈长 Under Neck Length	切深量 Depth of Cut		进给速度 Feed	主轴转速 Spindle Speed	切深量 Depth of Cut		进给速度 Feed	主轴转速 Spindle Speed	切深量 Depth of Cut		进给速度 Feed	主轴转速 Spindle Speed
		a_p mm	a_e mm	mm/min	min^{-1}	a_p mm	a_e mm	mm/min	min^{-1}	a_p mm	a_e mm	mm/min	min^{-1}
0.1	0.3	0.005	0.005	600	40,000	0.005	0.005	450	40,000	0.003	0.003	300	40,000
	0.6	0.005	0.005	500	40,000	0.005	0.005	350	40,000	0.003	0.003	250	40,000
0.15	0.3	0.005	0.005	800	40,000	0.005	0.005	600	40,000	0.003	0.003	450	40,000
	0.5	0.005	0.005	750	40,000	0.005	0.005	550	40,000	0.003	0.003	400	40,000
	0.75	0.005	0.005	700	40,000	0.005	0.005	500	40,000	0.003	0.003	400	40,000
0.2	0.5	0.005	0.01	1,200	40,000	0.005	0.01	900	40,000	0.005	0.005	600	40,000
	0.75	0.005	0.01	1,100	40,000	0.005	0.01	850	40,000	0.005	0.005	550	40,000
	1	0.005	0.01	1,000	40,000	0.005	0.01	800	40,000	0.005	0.005	500	40,000
	1.2	0.005	0.01	1,000	40,000	0.005	0.01	800	40,000	0.005	0.005	500	40,000
0.25	1	0.01	0.01	1,200	40,000	0.01	0.01	1,000	40,000	0.005	0.005	700	40,000
0.3	1.2	0.01	0.02	1,800	40,000	0.01	0.02	1,500	40,000	0.005	0.01	1,000	40,000
	1.5	0.01	0.02	1,500	40,000	0.01	0.02	1,200	40,000	0.005	0.01	800	40,000
0.4	1.6	0.01	0.02	1,800	40,000	0.01	0.02	1,500	40,000	0.005	0.01	1,000	40,000
	2	0.01	0.02	1,500	40,000	0.01	0.02	1,200	40,000	0.005	0.01	800	40,000
0.5	2	0.02	0.04	2,500	40,000	0.02	0.03	1,800	40,000	0.01	0.02	1,200	40,000
	2.5	0.02	0.04	2,000	40,000	0.02	0.03	1,500	40,000	0.01	0.02	1,000	40,000
0.6	2.4	0.02	0.04	2,500	40,000	0.02	0.03	2,000	40,000	0.01	0.02	1,500	40,000
	3	0.02	0.04	2,500	40,000	0.02	0.03	2,000	40,000	0.01	0.02	1,500	40,000
0.75	3	0.03	0.05	3,000	40,000	0.03	0.05	3,000	40,000	0.02	0.03	2,000	30,000
	3.8	0.03	0.05	3,000	40,000	0.03	0.05	3,000	40,000	0.02	0.03	2,000	30,000
1	4	0.05	0.1	3,000	30,000	0.03	0.05	3,000	30,000	0.03	0.03	2,000	25,000
	5	0.05	0.1	3,000	30,000	0.03	0.05	3,000	30,000	0.03	0.03	2,000	25,000
1.5	6	0.08	0.15	2,300	20,000	0.05	0.075	2,100	20,000	0.04	0.06	1,300	15,000
	9	0.06	0.12	2,200	20,000	0.04	0.06	2,000	20,000	0.04	0.05	1,200	15,000
2	8	0.1	0.18	2,300	17,000	0.06	0.09	2,100	15,000	0.05	0.07	1,300	12,000
	12	0.08	0.15	2,000	17,000	0.05	0.08	1,700	15,000	0.04	0.06	1,200	12,000
2.5	10	0.11	0.21	2,200	13,000	0.08	0.12	1,800	12,000	0.07	0.1	1,300	11,000
	15	0.1	0.18	1,900	13,000	0.06	0.1	1,500	12,000	0.06	0.08	1,100	11,000
3	12	0.13	0.24	2,000	10,000	0.09	0.15	1,600	10,000	0.08	0.12	1,200	10,000
	18	0.11	0.21	1,700	10,000	0.08	0.12	1,400	10,000	0.07	0.1	1,000	10,000

备注 Notes

※1 切深量为中精加工、精加工时的最大值。请根据机床刚性和要求精度进行调整。
※2 预加工（中精加工）时请注意精加工余量相对于加工面需保持均匀。
※3 R角等负载大的加工部位，请注意参数设定和刀路轨迹等。
※4 需要高品质的加工面时，加工时请将切深量调整为70%，进给速度调整为约70%。
※5 建议使用油雾冷却方式。
※6 因加工机床的原因要调整主轴转速时，必须按照相同的比率调整进给速度。

※1 Max. Depth of Cut for semi-finishing and finishing. Adjust milling conditions depending on the rigidity of the machine and desired accuracy.
※2 Obtain uniform stock amount on the cutting surface in the pre-stage cutting (semi-finishing).
※3 Required careful set up of milling conditions, tool path and etc. at cutting parts, such as corners where will become overloaded.
※4 Adjust both Depth of Cut and feed rate at 70% of the recommended milling conditions for high quality milling surface.
※5 Oil mist coolant is recommended.
※6 Adjust feed rate at same rate as spindle speed if necessary to adjust spindle speed from recommended milling conditions.

H ～52HRC 高硬度钢 Hardened Steel ◎
H ～60HRC 高硬度钢 Hardened Steel ◎
H ～65HRC 高硬度钢 Hardened Steel ◎
H ～70HRC 高硬度钢 Hardened Steel ◎

使用注意事项
Points in Use

加工环境 Advice on Cutting Environment

● 刀具偏摆量越小越好。
Minimize the deflection of cutting edge.

● 掌握机床主轴的伸缩量以及机床的水平状态，需要时采取恰当的措施。
To understand the nature of the expansion of the main spindle and machine posture transformation, and take measures against them.

精加工量(余量) Advice on Finishing Allowance (stock amount)

● 使用小径CBN铣刀时，精加工量(余量)均匀性非常重要。
When using small CBN End Mill, uniform finishing allowance (stock amount) is important.

● 粗加工・中精加工使用刀具磨损过大时，中精加工和精加工的余量会变大，从而影响刀具寿命和加工精度，所以预加工时留有均匀的加工余量非常重要。
When tool is used on roughing and semi-finishing and it has a big abrasion, finishing allowance (stock amount) on semi-finishing and finishing is increasing and it affects tool life and cutting accurary. Therefore, it is important to get uniform stock amount in the pre-stage cutting.

工件顶面 Top of work material
中精加工表面 Surface for semi-finishing
最终精加工表面 Surface for finishing
注意R角部位！ No uniformity at corner area

CBN
核心系列
CBN
Core Line